

NON-SHRINK GROUT



NON-SHRINK GROUT is a non shrink, high strength, non metallic, cementitious grouting compound used for a variety of general construction, grouting and anchoring applications which **NON-SHRINK GROUT** maintains its strengths at both flowable and trowelable consistencies.

- Anchoring bolts, posts and railings
- Structural columns
- Machinery bases
- Bearing plates
- Powerline stanchions
- Watertight
- Resists salt as well as many chemicals and oils
- Contains no chlorides, heavy metals or gypsum
- Non shrink
- Non bleeding
- Non segregating
- Meets ASTM C-1107
- Meets CRD C-621

Grout	May be poured or troweled
Packaging	50 lb bag (49/pallet)
Coverage	One 50 lb bag yields .45 cubic feet
Application Temperature	Ambient & surface temperature must be 40°F or above and will not fall below that for 48 hours
Mixing per 50 lb bag	<u>Trowelable</u> 4-1/2 quarts of water <u>Flowable</u> 6 quarts of water
Working Time	10-20 minutes at 70°F
Set Time	4 hours at 70°F
Color	Gray



Phone: 800-442-5535
 Fax: 978-453-2416
www.umaco.com